

# Wet Lamination Film BOPP Matte

## PCT-2(M)

### Structure



- Treated, glossy OPP layer
- Additive modified OPP core
- Treated, matte OPP layer

### Description

It is a co-extruded, plain, antistatic, both sides treated, one side matte, other side gloss Bi-axially Oriented Polypropylene film.

### Features

- Low static charge
- Excellent machinability
- Good ink / varnish adhesion
- High haze, good contact clarity

### Applications

- Natural look lamination of printed, unprinted paper, paperboard and carton lamination
- Extrusion coating with primer for thermo-lamination & UV spot coating.

### Typical values

Properties	Ref.	Units	ASTM#/ Test Method	PCT-2(M)				
<b>Physical Data</b>								
Average Thickness		Micron	D-374-C	12	13	15	18	20
		Gauge		48	52	60	72	80
		Mils		0.5	0.5	0.6	0.7	0.8
Thickness Variation		%(±)		3				
Density		g/cc		0.84				
Average substance		g/m <sup>2</sup>		10.0	10.9	12.6	15.1	16.8
Surface Tension(min)	Glossy	dynes/cm	D-2578	38				
Kinetic COF	Matte-Matte		D-1894	0.35 - 0.50				
Yield		m <sup>2</sup> /Kg	D-4321	100	91.7	79.3	66.2	59.5
		in <sup>2</sup> /lb		70307	64471	55753	46543	41832
<b>Optical Data</b>								
Gloss (45°)	Matte	Gardner	D-2457	7.0-10.0				
Haze		%	D-1003	68.0 - 75.0				
<b>Mechanical Data</b>								
Tensile Strength	MD	kg/cm <sup>2</sup>	D-882	1000-1400				
	TD			2400-2700				
Elongation	MD	%	D-882	130-180				
	TD			30-70				
<b>Thermal Data</b>								
Shrinkage (120°C/248 °F,5 min)	MD	%	D-1204	3.0-5.0				
	TD			1.0-3.0				

CTM : Cosmo Test Method

MD : Machine Direction

TD : Transverse Direction

**Disclaimer :** The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

**Storage condition :** Storage temperature to be maintained 25 Deg.C (+/-5 Deg C) & relative humidity 55% (+/-5%) to avoid accelerated reduction of surface treatment level.

**Cosmo Films Limited**

1st Floor, Uppal's Plaza, M-6 Jasola District Centre, New Delhi - 110025, India, T: + 91-11-49 49 49 49,

E-mail: sales.enquiry@cosmofilms.com | www.cosmofilms.com

Create Date : 2022-Aug-25